

Technical Data Sheet

Enke Primer PO

Product Description:

Enke Primer PO is a transparent, solvent-based, fast-drying synthetic resin solution, slightly yellowish in colour.

Properties:

Primer PO is an easily spreadable primer with excellent adhesion to a wide range of plastic sealing sheets of polyolefins, e.g. EPDM, FPO, etc.

Designated Use:

Use it as an adhesion promoter when applying ENKE roof coatings to plastic sheeting, e.g. of EPDM, FPE, FPO, PIB, TPE or TPO. Please refer to our Applications Engineering Department for suitable types of sheeting. Since the surface condition – and thus the adhesion – depends on the weathering condition, adhesion tests may be required.

Certification:



Application:

It is applied with a solvent-resistant fur roller or with a paint brush. In summer weather conditions Primer PO is dry after approximately 30 minutes and can be covered with a layer of an Enke roof coating.

Technical data:

Delivery form:	Low viscosity
Colour:	Yellowish-transparent
Flash-off time:	30–60 minutes (depending on weather)
Viscosity:	20–30 mPa·s at 20°C
Density:	Approx. 0.87 g/cm ³ at 20°C
Flash point:	Approx. 30°C

Consumption:

Approx. 50-100 g/m².

Delivery form:

2.5 kg disposable tin packing drum.

Storage:

Cool, in sealed original containers, protected from sunlight; for more information, see SDS.

Shelf life:

At least 12 months if stored properly.



LIQUID



Technical Data Sheet

Enke Primer PO

Disposal:

As soon as you have finished using the product, empty the packing drums completely to allow proper disposal, ensuring they are scraped out and drip-free. Tin containers emptied of residue can be recycled using appropriate steel recycling channels. As a certified user of the German recycling logo ENKE can provide a list of collection points.

The user shall dispose of non-hardened adhesive materials or larger amounts of product residues in tin containers at his costs as this is special waste.

MOY Materials Ltd has taken care to ensure that the information provided in the literature is correct and up to date. However, it is not intended to form any part of a contract or provide a guarantee. Purchasers/intending purchasers should contact MOY Technical to check whether there have been any changes to the information since publication of the literature. Please ensure you have read the hazard labels and material safety data sheet before using this product.